



SPECIFICATION FOR APPROVAL

Material

Production:	Sendust Cores
FUAN.P/N:	KS250-125A-E20
AL:	320(nH/N ²)±8%
Material:	125 μ
Coating Color:	Black
Coating material:	ероху
Coating Broakdown	Voltage: 1000V 0.5mA 25cc






Coating Breakdown Voltage: 1000V, 0.5mA, 2Sec

Physical Characteristics

Before Coating		After Coating						Weight			
OD(Max.) in/mm	ID(Min.) in/mm	Ht(Max.) in/mm	OD(Max.) mm	ID(Min.) mm	Ht(Max.) mm	Le(cm)	Ae(cm ²)	V(cm³)	W(cm²)	(g) (ref.)	Quantity (Pieces)
2.441 62.00	1.283 32.60	0.787	63.10	31.37	21.27	14.370	2.940	42.248	7.725	275.6	52

Electrical Parameters(Typical) Temperature(25°C±2°C)

Test Item	Test Condition	Value(Typical)	Test Instrument
Inductance	φ0.80mm/76Ts,20kHz/1V,I=0A (Evenly full windings)	1848µH±8%	CH3302
DC-Bias	φ0.80mm/76Ts,20kHz/1V,I=7.5A(H=50Oe) (Evenly full windings)	697.2µH(Min.)	WK3255B+WK3265B
Core Loss	50kHz/1000Gs	350mW/cm³(Max.)	SY-8219
Remarks	Set the internal resistance of LCR meter to 100Ω .		



Sendust Cores (KS Series) is made from 85% Fe, 9%Si and 6%Al. It named KoolMu by Magnetics. This material has low loss and relative high saturation flux density (10500Gs). it is very suitable for applying in PFC Chokes, Fly-back Transformers and Storage Filter Inductors. This soft magnetic material is magnetostriction is almost zero, so is special suitable for eliminating the In-line Noise Filters. Sendust Cores do not use organic binding material during the production, so it don' t does not have the problem of Thermal Aging. It can work in the environment of 200°C for a long time. Permeability that we can made now is 26ui-125ui in toroid, U type, E type and block. It is the best cost performance magnetic powder.